

ARMY RESEARCH LABORATORY



Laser Scattering Particle Size Distribution Analyses of Pigments

by Philip Patterson
and William Lum

ARL-TR-1786

September 1998

19980923 036

Approved for public release; distribution is unlimited.

DTIC QUALITY INSPECTED 1

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Abstract

The degree of pigment dispersion determines the coating's characteristics and performance. Through the use of the laser scattering particle size analyzer, measurements of particle size distribution range define the actual state of dispersion and, eventually, the characterization of military coating materials and other paint products. Standard materials (e.g., latex spheres of different particle sizes) were chosen to validate the operation of the instrument and to cover the wide dynamic range of the instrument's measurement and capability. Post-validation runs were made on several coating materials, including a polydispersed paint conforming to the U.S. Department of the Army military specification MIL-C-53039A, "Coating, Aliphatic Polyurethane, Single Component, Chemical Agent Resistant." This report details the instrumental parameters and sample preparation procedures used for the determinations. Additionally, the results of analysis are graphically displayed and discussed. A brief description of merited future work is also provided.

Table of Contents

	<u>Page</u>
List of Figures	v
1. Introduction	1
2. Approach	2
3. Experimental	3
4. Results	4
5. Conclusion	6
6. Future Work	10
7. References	11
Distribution List	13
Report Documentation Page	17

INTENTIONALLY LEFT BLANK.

List of Figures

<u>Figure</u>	<u>Page</u>
1. Horiba Model LA-900 Laser Scattering Particle Size Distribution Analyzer	2
2. Validation Run at Fort Belvoir, VA (Before Move) Standard	5
3. Validation Run After Move (APG Site) Standard	7
4. Particle Size Analysis of a TiO ₂ Sample	8
5. Particle Size Analysis of CARC Paint	9

INTENTIONALLY LEFT BLANK.

1. Introduction

An important step in the processing of protective coatings is the dispersion of the pigment particles within the resinous component of the system. When formulating these coatings, the pigment is usually dispersed in a portion of the vehicle (composed of the binder and solvent) by means of a high-speed mixer or mill. After milling, the homogeneity of pigment incorporation is oftentimes evaluated by measuring particle agglomerates. Excess particle agglomeration can have detrimental effects on the appearance, as well as the optical and rheological properties of the final paint product.

A method for measuring these oversized particles involves the use of a fineness of grind gauge. The test for determining fineness of grind, or degree of dispersion, is performed by spreading a portion of the coating along a calibrated, depth-tapered path. At some point along this path, oversized particles or agglomerates will become visible. A numerical value in Hegman scale or micron units is taken from the calibrated scale at the point where the particles form a definite pattern. The American Society for Testing and Materials (ASTM) (1996) Method D-1210-79 (reapproved 1988) "Standard Test Method for Fineness of Dispersion of Pigment - Vehicle Systems" is a commonly referenced procedure for this type of evaluation. And although the test is simple and inexpensive to perform, it is somewhat limited in scope. The technique is nonquantitative and gives, at best, only an indication of particles whose dimensions are about 10 μ or greater. Since many of the prime pigments used in the U.S. Army's camouflage topcoats are less than 10 μ , the grind gauge cannot accurately detect all of these sized particles.

Additionally, a single value is generated using a grind gauge for a given coating formulation. However, since pigments of various dimensions exist within the coating matrix, a measurement involving a particle size distribution range would more thoroughly define the actual state of dispersion. This study involves the use of such a measurement device, the classical angular laser scattering particle size analyzer. This instrument will be used to perform particle size distribution analysis for the characterization of military coating materials and paint products.

2. Approach

The instrument that was used for authors' preliminary analyses was the Horiba Model LA-900 laser scattering particle size distribution analyzer (Horiba Instruments Incorporated, Irvine, CA) (Figure 1). Based on Gustave Mie scattering theory of measurement, particles suspended in a liquid as small as $0.04\ \mu\text{m}$ can be determined. The LA-900 instrument takes advantage of this theory by using front, side, and rear scatter detectors. Then, the Mie theory is drawn upon to calculate the particle size distribution of a given sample. Measurement is possible on the Horiba LA-900 over a wide range from $0.04\ \mu\text{m}$ to $1,000\ \mu\text{m}$, which is a huge advantage over the grind gauge or even the coarse particle sieve.



Figure 1. Horiba Model LA-900 Laser Scattering Particle Size Distribution Analyzer.

A fraction cell with a magnetic stirrer in a cell holder was the sampling option selected for use over a circulation cell or flow cell. This allows the measurement of minute quantities of a sample without loss of the sample material. Also, the rapid deterioration of seals and tubing due to the kinds of particles and dispersants used is a major drawback, if circulating techniques are chosen.

Standard materials, such as monodispersed polystyrene latex spheres from Duke Scientific Corporation, Palo Alto, CA, were chosen to validate the operation of the instrument. These materials are used for total performance testing of the entire system's operation and should produce very narrow distribution results.

The software that generated the graphics display and performed the instrument control and data calculation was the Horiba LA-900 Measure Version 2.00d and the Horiba LA-900 Refraction Indices Version 2.00d. The software and operation are interfaced with Microsoft Windows operating system Version 3.0. All program software was loaded on a Compaq Prolinea 486/33-mHz desktop computer. Normal measurement time is approximately 30 s per run.

3. Experimental

Standard materials from Duke Scientific Corporation were procured at different particle sizes to cover the wide range of measurement and the instrument's capability. The recommended series of size standards are 102 nm, 503 nm, 0.993 μm , 9.975 μm , and 100 μm . This phase is a critical preliminary step in which the standard runs validate the instrument's condition and operation, as well as assure the proper setup procedures when using a fraction cell.

Duke Scientific products are packaged as aqueous suspensions in dropper-tipped vials. Three or four drops of the standard suspension in a deionized (DI)-water-filled fraction cell will place it at the right concentration or loading for measurement.

The conditions were given by Duke Scientific to run standards as follows: set the relative refractive index at 1.19–9.99i and the form of distribution at 3. These instrument settings are recommended when analyzing nearly ideal samples. That is, when the particles are small, spherical, and transparent and have a very narrow range of distribution. Also of note, only DI water was used as the dispersing fluid or dispersant. No surfactants (cationic, anionic, or nonionic) were added to the standard solutions.

When the authors were satisfied with the standard runs' results, particle size determinations were made on titanium dioxide (TiO_2) pigment, a major component in most chemical agent resistant coating (CARC) primer and desert-colored paints. A TiO_2 hand-mixed slurry was dispersed by using DuPont Pigments and Dispersions, Inc., Wilmington, DE, Ti-Pure R960 in Reichhold Chemical Products Company, Pittsburgh, PA, no. 6440 alkyd resin (1:1 ratio) with methyl ethyl ketone and methyl (MEK) iso-butyl ketone solvent system (1:1:1/2:1/10 ratio, respectively).

The next logical step was to analyze a typical "wet" paint sample. A polyurethane topcoat conforming to the military coating specification MIL-C-53039A "Coating, Aliphatic Polyurethane, Single Component, Chemical Agent Resistant," (U.S. Department of the Army 1989) was selected for the trial runs. These coating analyses were not made to yield absolute particle size determinations, but rather to give the analysts an idea of the type of data that could be obtained, as well as to develop a reliable sampling technique when dealing with viscous materials. The samples were prepared by an initial dilution with MEK in a given ratio of 0.5:1. After thorough mixing, additional MEK was added to optimize the concentration level. This level is readily verified by placing the diluted sample into the instrument's light path and checking the degree of transmittance (about 80–90% T). This dilution process also worked well when preparing and analyzing other coating materials, such as carbazole violet, a minor but very important camouflage tinting pigment found in several Green 383 CARC formulations.

4. Results

Figure 2 represents an initial validation run using polystyrene microspheres. The particle size standard (lot no. 18267) was certified to have a mean diameter of $0.993 \mu\text{m} \pm 0.021 \mu\text{m}$ with a standard deviation of $0.010 \mu\text{m}$ and a coefficient of variation equal to 1.0%. Measurements were made via surface analyzer techniques. As shown, the results obtained from the LA-900 laser scattering particle size analyzer are consistent with the size limits set forth by the supplier $\pm 10\%$ error and $< 5\%$ spread range, respectively.

Horiba Instruments, Inc.

LA-900 Laser Scattering Particle Size Distribution Analyzer


Analysis Report

Jul/24/98

Sample	: philstd2.dat	Material	:
ID#	: 970218-263	Source	:
Filename	: PHILSTD2.DAT	lot Number	:
Version	: 2.00d Orig: 1.10	Operator	:

Condition			
T % (He-Ne)	: 94.8%	Dist. Form	: 3
(LAMP)	: 93.1%	R.R. Index	: 1.19 - 9.99i
Agitation	: 0	Circuln	: 0
		Sampling times	: 15
		U.sonic	: OFF (5) (min)
		U.sonic Wait	: 0 (sec)

Data - Volume			
Median	: 1.004 μ m	Mean	: 0.998 μ m
		S.D.	: 0.117 μ m
		SP. Area	: 60996 cm ² /cm ³
Dia. on % (10.0%)	: 1.140 μ m	% on Dia. (10.000 μ m)	: 0.0%
Dia. on % (30.0%)	: 1.070 μ m		
Dia. on % (50.0%)	: 1.004 μ m		
Dia. on % (70.0%)	: 0.932 μ m		
Dia. on % (90.0%)	: 0.839 μ m		



Size (μm)	Freq (%)	Ovr (%)	Size (μm)	Freq (%)	Ovr (%)	Size (μm)	Freq (%)	Ovr (%)
1019.5	0.00	0.00	34.25	0.00	0.00	1.150	42.56	7.23
890.1	0.00	0.00	29.90	0.00	0.00	1.004	36.68	49.80
777.1	0.00	0.00	26.11	0.00	0.00	0.877	10.84	86.48
678.5	0.00	0.00	22.79	0.00	0.00	0.765	1.99	97.32
592.3	0.00	0.00	19.90	0.00	0.00	0.668	0.52	99.31
517.2	0.00	0.00	17.37	0.00	0.00	0.583	0.15	99.84
451.5	0.00	0.00	15.17	0.00	0.00	0.509	0.00	100.00
394.2	0.00	0.00	13.24	0.00	0.00	0.445	0.00	100.00
344.2	0.00	0.00	11.56	0.00	0.00	0.388	0.00	100.00
300.5	0.00	0.00	10.09	0.00	0.00	0.339	0.00	100.00
262.3	0.00	0.00	8.815	0.00	0.00	0.296	0.00	100.00
229.0	0.00	0.00	7.696	0.00	0.00	0.258	0.00	100.00
200.0	0.00	0.00	6.719	0.00	0.00	0.225	0.00	100.00
174.6	0.00	0.00	5.866	0.00	0.00	0.197	0.00	100.00
152.4	0.00	0.00	5.122	0.00	0.00	0.172	0.00	100.00
133.1	0.00	0.00	4.472	0.00	0.00	0.150	0.00	100.00
116.2	0.00	0.00	3.904	0.00	0.00	0.131	0.00	100.00
101.4	0.00	0.00	3.408	0.00	0.00	0.114	0.00	100.00
88.58	0.00	0.00	2.976	0.00	0.00	0.100	0.00	100.00
77.33	0.00	0.00	2.598	0.00	0.00	0.087	0.00	100.00
67.52	0.00	0.00	2.268	0.00	0.00	0.076	0.00	100.00
58.95	0.00	0.00	1.980	0.00	0.00	0.066	0.00	100.00
51.47	0.00	0.00	1.729	0.00	0.00	0.058	0.00	100.00
44.93	0.00	0.00	1.509	0.00	0.00	0.050	0.00	100.00
39.23	0.00	0.00	1.318	7.23	0.00			

Figure 2. Validation Run at Fort Belvoir, VA (Before Move) Standard. From Duke Scientific Corporation, Palo Alto, CA, Polymer Microspheres Lot No. 18267 0.993 μ m \pm 0.021 μ m.

Figure 3 represents an additional validation run on another microsphere standard (lot no. 18401) having a mean diameter of $9.975\ \mu\text{m} \pm 0.061\ \mu\text{m}$. As before, the analyzed median diameter of $10.48\ \mu\text{m}$ is within the expected size and spread range limitations. Noteworthy is that these analyses were performed in two different laboratories. The initial validation run (Figure 2) was performed at the Communications and Electronics Command's (CECOM) Research, Development, and Engineering Center located at Fort Belvoir, VA. The Figure 3 analysis was performed at the U.S. Army Research Laboratory (ARL) (Bldg. 4600), Aberdeen Proving Ground (APG), MD. The dual-location analyses were a result of a mission transfer due to the Base Realignment and Closure Act (BRAC). The quality of the validation data obtained indicated that the instrument's condition was not adversely affected during the relocation process between laboratories.

Figure 4 represents the particle size analysis of the TiO_2 pigment sample, dispersed as previously discussed. As shown, the median particle diameter was measured at $0.48\ \mu\text{m}$. This is in close agreement, within 5%, of the manufacturer's reported value of $0.50\ \mu\text{m}$. It should be noted that the manufacturer's technique for measuring particle size was light microscopy. The analyst should be aware that each measurement technique detects size through its own physical principle and that no single instrument can provide a universal answer.

Figure 5 represents the particle size distribution analysis of the selected whole paint. This tan-colored solvent-based coating contains pigment particles of various sizes, shapes, and chemical compositions. Upon inspection, the graph quite clearly shows a well-resolved multimodal distribution with particle sizes ranging from approximately $0.1\ \mu\text{m}$ to $50\ \mu\text{m}$. And although the shape of the graph does indeed represent a polydispersed system, the actual diameter values must be considered with care since the conversion algorithm or mathematical function used for the light scattering has not been thoroughly reviewed for bias.

5. Conclusion

Laser-light scattering shows promise as a reliable method when performing particle size analysis on coatings and related materials. A wide dynamic range ($0.1\text{--}1,000\ \mu\text{m}$) of particle sizes can be

Horiba Instruments, Inc.

Analysis Report


LA-900 Laser Scattering Particle Size Distribution Analyzer

Jul/24/98

Sample	:		Material	:	
ID #	:	970219-269	Source	:	
Filename	:	PHILSTD3.DAT	lot Number	:	
Version	:	2.00d Orig: 1.10	Operator	:	

Condition					
T % (He-Ne)	:	93.6 %	Dist. Form	:	3
(LAMP)	:	96.6 %	R.R. Index	:	1.19 - 9.99i
Agitation	:	0	Circuln	:	0
			Sampling times	:	15
			U.sonic	:	OFF (5) (min)
			U.sonic Wait	:	0 (sec)

Data - Volume					
Median	:	10.458 μ m	Mean	:	10.292 μ m
			S.D.	:	1.255 μ m
			SP. Area	:	5935 cm ² /cm ³
Dia. on % (10.0 %)	:	11.498 μ m	% on Dia. (10.000 μ m)	:	66.3 %
Dia. on % (30.0 %)	:	10.966 μ m			
Dia. on % (50.0 %)	:	10.458 μ m			
Dia. on % (70.0 %)	:	9.758 μ m			
Dia. on % (90.0 %)	:	8.436 μ m			



Size (μm)	Freq (%)	Ovr (%)	Size (μm)	Freq (%)	Ovr (%)	Size (μm)	Freq (%)	Ovr (%)
1019.5	0.00	0.00	34.25	0.00	0.00	1.150	0.00	100.00
890.1	0.00	0.00	29.90	0.00	0.00	1.004	0.00	100.00
777.1	0.00	0.00	26.11	0.00	0.00	0.877	0.00	100.00
678.5	0.00	0.00	22.79	0.00	0.00	0.765	0.00	100.00
592.3	0.00	0.00	19.90	0.00	0.00	0.668	0.00	100.00
517.2	0.00	0.00	17.37	0.00	0.00	0.583	0.00	100.00
451.5	0.00	0.00	15.17	2.03	0.00	0.509	0.00	100.00
394.2	0.00	0.00	13.24	5.53	2.03	0.445	0.00	100.00
344.2	0.00	0.00	11.56	57.29	7.56	0.388	0.00	100.00
300.5	0.00	0.00	10.09	20.44	64.85	0.339	0.00	100.00
262.3	0.00	0.00	8.815	14.48	85.30	0.296	0.00	100.00
229.0	0.00	0.00	7.696	0.00	99.79	0.258	0.00	100.00
200.0	0.00	0.00	6.719	0.00	99.79	0.225	0.00	100.00
174.6	0.00	0.00	5.866	0.00	99.79	0.197	0.00	100.00
152.4	0.00	0.00	5.122	0.00	99.79	0.172	0.00	100.00
133.1	0.00	0.00	4.472	0.00	99.79	0.150	0.00	100.00
116.2	0.00	0.00	3.904	0.00	99.79	0.131	0.00	100.00
101.4	0.00	0.00	3.408	0.00	99.79	0.114	0.00	100.00
88.58	0.00	0.00	2.976	0.20	99.79	0.100	0.00	100.00
77.33	0.00	0.00	2.598	0.00	100.00	0.087	0.00	100.00
67.52	0.00	0.00	2.268	0.00	100.00	0.076	0.00	100.00
58.95	0.00	0.00	1.980	0.00	100.00	0.066	0.00	100.00
51.47	0.00	0.00	1.729	0.00	100.00	0.058	0.00	100.00
44.93	0.00	0.00	1.509	0.00	100.00	0.050	0.00	100.00
39.23	0.00	0.00	1.318	0.00	100.00			

Figure 3. Validation Run After Move (APG Site) Standard. From Duke Scientific Corporation, Palo Alto, CA, Polymer Microspheres Lot No. 118401 9.975 μ m \pm 0.61 μ m.

Horiba Instruments, Inc.

Analysis Report


LA-900 Laser Scattering Particle Size Distribution Analyzer

Jul/27/98

Sample	: TiO ₂ Sample	Material	: Dispersion
ID#	: 980706-236-12:59:18	Source	: DuPont Ti-Pure
Filename	: TITAN.DAT	lot Number	:
Version	: 2.00d	Operator	: PHP

Condition			
T% (He-Ne)	: 117.6%	Dist. Form	: 2
(LAMP)	: 94.2%	R.R. Index	: 1.85 - 0.00i
Agitation	: 0	Circuitn	: 0
		Sampling times	: 15
		U.sonic	: OFF (5) (min)
		U.sonic Wait	: 0 (sec)

Data - Volume			
Median	: 0.480 μ m	Mean	: 0.483 μ m
		S.D.	: 0.093 μ m
		SP. Area	: 129456 cm ² /cm ³
Dia. on % (10.0%)	: 0.609 μ m	% on Dia. (10.000 μ m)	: 0.0%
Dia. on % (30.0%)	: 0.531 μ m		
Dia. on % (50.0%)	: 0.480 μ m		
Dia. on % (70.0%)	: 0.433 μ m		
Dia. on % (90.0%)	: 0.362 μ m		



Size (μm)	Freq (%)	Ovr (%)	Size (μm)	Freq (%)	Ovr (%)	Size (μm)	Freq (%)	Ovr (%)
1019.5	0.00	0.00	34.25	0.00	0.00	1.150	0.00	0.00
890.1	0.00	0.00	29.90	0.00	0.00	1.004	0.00	0.00
777.1	0.00	0.00	26.11	0.00	0.00	0.877	0.12	0.00
678.5	0.00	0.00	22.79	0.00	0.00	0.765	2.02	0.12
592.3	0.00	0.00	19.90	0.00	0.00	0.668	11.46	2.15
517.2	0.00	0.00	17.37	0.00	0.00	0.583	23.57	13.61
451.5	0.00	0.00	15.17	0.00	0.00	0.509	29.23	37.19
394.2	0.00	0.00	13.24	0.00	0.00	0.445	19.12	66.42
344.2	0.00	0.00	11.56	0.00	0.00	0.388	8.66	85.55
300.5	0.00	0.00	10.09	0.00	0.00	0.339	3.42	94.21
262.3	0.00	0.00	8.815	0.00	0.00	0.296	1.43	97.64
229.0	0.00	0.00	7.696	0.00	0.00	0.258	0.63	99.07
200.0	0.00	0.00	6.719	0.00	0.00	0.225	0.28	99.71
174.6	0.00	0.00	5.866	0.00	0.00	0.197	0.00	100.00
152.4	0.00	0.00	5.122	0.00	0.00	0.172	0.00	100.00
133.1	0.00	0.00	4.472	0.00	0.00	0.150	0.00	100.00
116.2	0.00	0.00	3.904	0.00	0.00	0.131	0.00	100.00
101.4	0.00	0.00	3.408	0.00	0.00	0.114	0.00	100.00
88.58	0.00	0.00	2.976	0.00	0.00	0.100	0.00	100.00
77.33	0.00	0.00	2.598	0.00	0.00	0.087	0.00	100.00
67.52	0.00	0.00	2.268	0.00	0.00	0.076	0.00	100.00
58.95	0.00	0.00	1.980	0.00	0.00	0.066	0.00	100.00
51.47	0.00	0.00	1.729	0.00	0.00	0.058	0.00	100.00
44.93	0.00	0.00	1.509	0.00	0.00	0.050	0.00	100.00
39.23	0.00	0.00	1.318	0.00	0.00			

Figure 4. Particle Size Analysis of a TiO₂ Sample.

Horiba Instruments, Inc.

Analysis Report


LA-900 Laser Scattering Particle Size Distribution Analyzer

Jul/24/98

Sample	: Deft Q 170 46168 A/C Gray	Material	:
ID#	: 950801-149	Source	:
Filename	: 1ACD0002.DAT	lot Number	:
Version	: 2.00d Orig: 1.10	Operator	:

Condition			
T% (He-Ne)	: 75.4%	Dist. Form	: 1
(LAMP)	: 79.0%	R.R. Index	: 1.32 - 0.00i
Agitation	: 0	Circuitn	: 0
		Sampling times	: 15
		U. sonic	: OFF (5) (min)
		U. sonic Wait	: 0 (sec)

Data - Volume			
Median	: 6.441 μ m	Mean	: 7.484 μ m
		S.D.	: 7.365 μ m
		SP. Area	: 80571 cm ² /cm ³
Dia. on % (10.0%)	: 0.219 μ m	% on Dia. (10.000 μ m)	: 65.4%
Dia. on % (30.0%)	: 1.002 μ m		
Dia. on % (50.0%)	: 6.441 μ m		
Dia. on % (70.0%)	: 10.983 μ m		
Dia. on % (90.0%)	: 17.298 μ m		



Size (μm)	Freq (%)	Und (%)	Size (μm)	Freq (%)	Und (%)	Size (μm)	Freq (%)	Und (%)
1019.5	0.00	100.00	34.25	0.52	99.58	1.150	0.92	30.93
890.1	0.00	100.00	29.90	0.94	99.06	1.004	0.72	30.00
777.1	0.00	100.00	26.11	1.62	98.11	0.877	0.55	29.28
678.5	0.00	100.00	22.79	2.57	96.48	0.765	0.42	28.73
592.3	0.00	100.00	19.90	3.74	93.91	0.668	0.31	28.31
517.2	0.00	100.00	17.37	5.00	90.16	0.583	0.25	27.99
451.5	0.00	100.00	15.17	6.07	85.16	0.509	0.26	27.73
394.2	0.00	100.00	13.24	6.59	79.09	0.445	0.39	27.47
344.2	0.00	100.00	11.56	6.58	72.50	0.388	0.85	27.07
300.5	0.00	100.00	10.09	6.01	65.91	0.339	2.19	26.22
262.3	0.00	100.00	8.815	5.07	59.90	0.296	4.97	24.02
229.0	0.00	100.00	7.696	3.91	54.82	0.258	7.64	19.05
200.0	0.00	100.00	6.719	2.90	50.90	0.225	6.80	11.40
174.6	0.00	100.00	5.866	2.10	48.00	0.197	3.58	4.60
152.4	0.00	100.00	5.122	1.52	45.89	0.172	0.87	1.01
133.1	0.00	100.00	4.472	1.22	44.36	0.150	0.14	0.14
116.2	0.00	100.00	3.904	1.08	43.14	0.131	0.00	0.00
101.4	0.00	100.00	3.408	1.04	42.06	0.114	0.00	0.00
88.58	0.00	100.00	2.976	1.18	41.01	0.100	0.00	0.00
77.33	0.00	100.00	2.598	1.36	39.82	0.087	0.00	0.00
67.52	0.00	100.00	2.268	1.63	38.45	0.076	0.00	0.00
58.95	0.00	100.00	1.980	1.71	36.82	0.066	0.00	0.00
51.47	0.00	100.00	1.729	1.61	35.10	0.058	0.00	0.00
44.93	0.13	100.00	1.509	1.39	33.49	0.050	0.00	0.00
39.23	0.27	99.86	1.318	1.15	32.09			

Figure 5. Particle Size Analysis of a CARC Paint.

determined in a single measurement on a variety of coating products and raw materials. Measurement times are fast (typically 20–40 s), allowing for the possibility of a high-volume sample turnaround capability. Instrument operation can be quickly learned, the software is user-friendly, and checking the system's performance is easily verified by using routine control materials. Small and/or hazardous samples can be analyzed with the use of a fraction cell.

As with any new laboratory technique, the analyst should be aware of the limitations of the instrument's capability. Errors in size distribution results obtained from light scattering measurements primarily involve the optical arrangement of the instrument's multidetector and the matrix conversion (especially, the complex optical correction model) algorithm or mathematical function chosen by the user during data retrieval.

6. Future Work

Particle size analysis will continue using the static laser-light scattering technique with the focus on camouflage coating samples and their relative degree of pigment dispersion. Special attention will be given to which optical model is best suited for converting the light scattering data into the corresponding size distribution. For a given analysis, an improper optical model selection can be monitored by observing the resulting distribution graph for (1) multiple artificial peaks, (2) excessive peak broadening, and/or (3) incorrect reporting of median, mean, and mode particle size data.

Further, since the light scattering measurements are based on the optical properties of the particle, a greater emphasis will be placed on choosing the sample's relative refractive index value, as well as its imaginary factor value. The selection of the proper value is a vital key in obtaining accurate size distribution for a given dispersion.

Also of interest is the evaluation of particle size determinations when coupled with data obtained from other coating characterization techniques, such as film surface imaging and profiling.

7. References

- American Society for Testing and Materials. "Standard Test Method for Fineness of Dispersion of Pigment - Vehicle Systems." ASTM D1210-79, *1996 Annual Book of Standards*, vol. 06.01, pp. 106-113, 1996.
- U.S. Department of the Army. "Coating, Aliphatic Polyurethane, Single Component, Chemical Agent Resistant." Military Specification MIL-C-53039A, 1 August 1989.

INTENTIONALLY LEFT BLANK.

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFORMATION CENTER DTIC DDA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDQ DENNIS SCHMIDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	OSD OUSD(A&T)/ODDDR&E(R) R J TREW THE PENTAGON WASHINGTON DC 20301-7100
1	CECOM SP & TRRSTRL COMMCTN DIV AMSEL RD ST MC M H SOICHER FT MONMOUTH NJ 07703-5203
1	PRIN DPTY FOR TCHNLGY HQ US ARMY MATCOM AMCDCG T M FISETTE 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	DPTY CG FOR RDE HQ US ARMY MATCOM AMCRD MG BEAUCHAMP 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	INST FOR ADVNCD TCHNLGY THE UNIV OF TEXAS AT AUSTIN PO BOX 202797 AUSTIN TX 78720-2797
1	GPS JOINT PROG OFC DIR COL J CLAY 2435 VELA WAY STE 1613 LOS ANGELES AFB CA 90245-5500

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DARPA B KASPAR 3701 N FAIRFAX DR ARLINGTON VA 22203-1714
1	NAVAL SURFACE WARFARE CTR CODE B07 J PENNELLA 17320 DAHLGREN RD BLDG 1470 RM 1101 DAHLGREN VA 22448-5100
1	US MILITARY ACADEMY MATH SCI CTR OF EXCELLENCE DEPT OF MATHEMATICAL SCI MDN A MAJ DON ENGEN THAYER HALL WEST POINT NY 10996-1786
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CS AL TA 2800 POWDER MILL RD ADELPHI MD 20783-1145
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1145
	<u>ABERDEEN PROVING GROUND</u>
4	DIR USARL AMSRL CI LP (305)

NO. OF COPIES	ORGANIZATION
1	OUSD AT STRT TAC SYS DR SCHNEITER RM 3E130 3090 DEFENSE PENTAGON WASHINGTON DC 20310-3090
1	OASD C31 DR SOOS RM 3E194 6000 DEFENSE PENTAGON WASHINGTON DC 20301-6000
1	UNDER SEC OF THE ARMY DUSA OR ROOM 2E660 102 ARMY PENTAGON WASHINGTON DC 20310-0102
1	ASST SECY ARMY RESEARCH DEVELOPMENT ACQUISITION SARD ZD ROOM 2E673 103 ARMY PENTAGON WASHINGTON DC 20310-0103
1	ASST SECY ARMY RESEARCH DEVELOPMENT ACQUISITION SARD ZP ROOM 2E661 103 ARMY PENTAGON WASHINGTON DC 20310-0103
1	ASST SECY ARMY RESEARCH DEVELOPMENT ACQUISITION SARD ZS ROOM 3E448 103 ARMY PENTAGON WASHINGTON DC 20310-0103
1	OADCSOPS FORCE DEV DIR DAMO FDZ ROOM 3A522 460 ARMY PENTAGON WASHINGTON DC 20310-0460
1	OADCSOPS FORCE DEV DIR DAMO FDW RM 3C630 460 ARMY PENTAGON WASHINGTON DC 20310-0460

NO. OF COPIES	ORGANIZATION
1	HQ USAMC DEP CHF OF STAFF FOR RDA AMCRD 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	ARMY TRNG & DOCTRINE COM ATCD B FT MONROE VA 23561-5000
1	ARMY TRADOC ANL CTR ATRC W MR KEINTZ WSMR NM 88002-5502
1	ARMY RESEARCH LABORATORY AMSRL SL PLANS AND PGMS MGR WSMR NM 88002-5513
1	ARMY RESEARCH LABORATORY AMSRL SL E MR SHELBURNE WSMR NM 88002-5513
1	ARMY RESEARCH LABORATORY AMSRL ST DR ROCCHIO 2800 POWDER MILL RD ADELPHI MD 20783-1197

NO. OF
COPIES ORGANIZATION

1 ABERDEEN PROVING GROUND
ARMY TEST EVAL COM
AMSTE TA
APG MD 21005-5055

1 US ARMY EVAL ANALYSIS CTR
CSTE EAC MR HUGHES
4120 SUSQUEHANNA AVE
APG MD 21005-3013

1 US ARMY EVAL ANALYSIS CTR
CSTE EAC SV DR HASKELL
4120 SUSQUEHANNA AVE
APG MD 21005-3013

1 ARMY RESEARCH LABORATORY
AMSRL SL
DR WADE
APG MD 21005-5068

2 ARMY RESEARCH LABORATORY
AMSRL SL B
MS SMITH
W WINNER
APG MD 21005-5068

1 ARMY RESEARCH LABORATORY
AMSRL SL E
DR STARKS
APG EA MD 21010-5423

NO. OF
COPIES ORGANIZATION

5	CDR USA TACOM AMSTA JSK S GOODMAN AMSTA TBI S HOFFMAN AMSTA TR W WHEELLOCK AMSTA D COL SCHREPPLE AMSTA TR R J PARKS WARREN MI 48397-5000
3	CDR USA TACOM AMSAT G AMSAT R ZT R KENNEDY AMSAT D TS W KILLIAN 4300 GOODFELLOW BLVD ST LOUIS MO 63120-1798
2	CDR WRIGHT PATTERSON AFB WL FIV A MAYER WL MLBM S DONALDSON 2941 P STREET STE 1 DAYTON OH 45433
1	DIR USARL PROGRAMS AND PLANS MGR AMSRL SL WSMR NM 88002-5513
1	ARMY TRADOC ANL CTR ATRC W MR KEINTZ WSMR NM 88002-5502
2	CDR HQ AMCCOM AMSMC LSL B KELEBER AMSMC SAS WF G SCHELENKER ROCK ISLAND IL 61299-6000
1	CDR USARO TECH LIB D MANN PO BOX 12211 RESEARCH TRIANGLE PARK NC 27709-2211
1	CDR NSWC CODE E23 TECH LIBRARY DAHLGREN VA 22448-5000

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
<small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project(0704-0188), Washington, DC 20503.</small>				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE September 1998	3. REPORT TYPE AND DATES COVERED Final, Jan 97-Dec 97	
4. TITLE AND SUBTITLE Laser Scattering Particle Size Distribution Analyses of Pigments			5. FUNDING NUMBERS ARL-3261	
6. AUTHOR(S) Philip Patterson and William Lum				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-MA Aberdeen Proving Ground, MD 21005-5069			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-1786	
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) The degree of pigment dispersion determines the coating's characteristics and performance. Through the use of the laser scattering particle size analyzer, measurements of particle size distribution range define the actual state of dispersion and, eventually, the characterization of military coating materials and other paint products. Standard materials (e.g., latex spheres of different particle sizes) were chosen to validate the operation of the instrument and to cover the wide dynamic range of the instrument's measurement and capability. Post-validation runs were made on several coating materials, including a polydispersed paint conforming to the U.S. Department of the Army military specification MIL-C-53039A, "Coating, Aliphatic Polyurethane, Single Component, Chemical Agent Resistant," 1 August 1989. This report details the instrumental parameters and sample preparation procedures used for the determinations. Additionally, the results of analysis are graphically displayed and discussed. A brief description of merited future work is also provided.				
14. SUBJECT TERMS particle size, laser-light scattering, coatings, pigments			15. NUMBER OF PAGES 20	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-1786 (Patterson) Date of Report September 1998

2. Date Report Received _____

3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)

(DO NOT STAPLE)